

*Get wise with the Next Generation.  
CoverWise™ Olefin Film looks,  
feels, and performs like vinyl!*

**CoverWise™ Olefin Film**

**Olefin-based system free of Plasticizers!**

**Look & Feel!**

Our olefin film looks, feels and processes like vinyl, yet provides the durability of an olefin. Color, embossing and other vinyl specifications are formulated to your requirements.

**Performance**

Formulations available to meet a variety of flame and mold requirements. Unlike other olefins, our film does not drip when exposed to heat or flame.

**Low Volatility**

Our Olefin film has low smoke and odor when processed at elevated temperatures.

**Superior Cold Crack**

Performs in cold environments as low as -50°F.

**Superior Printability vs. other Olefins**

Crisp, clean printing with water or solvent-based inks.

**CoverWise™ Olefin Film meets or exceeds:**

All Type II Certifications  
Class "A" flame rating – ASTM E-84 Test

**Improved Environmental Processing**



**CoverWise™ Films**

**Customized Solutions  
for Commercial Wallcovering**

Use PolyOne CoverWise™ Films for Interior Solutions including wallcoverings, flooring, window shades, wood laminates, and specialty applications. PolyOne offers numerous vinyl and olefin films.

| Property              | Test Method              | Standard                     | Coverwise™ Olefin Results* |
|-----------------------|--------------------------|------------------------------|----------------------------|
| Elongation at Break   | ASTM D882                | 250% min.                    | 600%                       |
| Tensile at Break      | ASTM D882                | 3000 lb/in <sup>2</sup> min. | 3000 lb/in <sup>2</sup>    |
| Tear Strength         | ASTM D1004               | 60 lb/in <sup>2</sup> min.   | 70 lb/in <sup>2</sup>      |
| Cold Crack Resistance | FLTM BN102-01            | No change at +20°F           | -50°F                      |
| Flammability          | ASTM E-84                | Flame = 25<br>Smoke = 50     | Flame = 25<br>Smoke = 15   |
| Mold Growth           | ASTM G21                 | 0 to 1 (no growth)           | 1                          |
| Dimensional Stability | Federal Spec. CCC-W-408D | -2.0% Max                    | -1.0 %                     |

\* Typical test results for commercial wallcovering (0.010" Opaque Film). Values considered to be nominal and do not constitute a warranty, specification, or fitness for particular purpose.

For More Information Contact:

**O'Sullivan Films**

Phone: 800-894-0426  
Fax: 540-722-2695  
joe.cipullo@osul.com  
www.osul.com